



**** GET-A-BOND ****

A Multi Purpose Adhesive & Bonding Agent

PRODUCTION DESCRIPTION :-

Get-a-bond is a multi purpose adhesive and bonding agent. Get-a-bond will bond most common building materials to them selves or to each other provided one surface is porous. Get-a-bond will not bond two impervious surfaces no PVC, ABS, application is building industry. Get-a-bond improves the workability of cement mortars and has many applications in the building industry.

SPECIAL FEATURES :-

- Single component, PVA based.
- Excellent bond to concrete, masonry, stone work, plaster and block board.
- Reduces permeability of cement mortars.
- Improve tensile and flexural strength.
- Compatible with common hydraulic cement.
- Get-a-bond is economical to use.

AREA OF USE :-

Renderings, mortars and slurries. Repair of worn, damaged and spalled concrete. For improving and bonding floor topping, bonding of slip bricks and tiles.

PRODUCT DATA :-

APPEARANCE	:	Milky White.
CONSISTENCY	:	Viscous material .
VOLUME SOLID	:	34 %
PRODUCT WEIGHT	:	1.05 kg/ltr.
VISCOSITY	:	27 – 32 Poise R/T.
FLASH POINT	:	Non-flammable (water-borne product)

SURFACE PREPARATION :-

Surface must be clean and sound. Remove oil, greasy unsound concrete, loose materials and foreign matters with compressed air. Surface uniformly with water before use.



APPLICATION DETAILS :-

Blend cement and sand separately. Add Getabond and water mixed together. If necessary add more water until the desired consistency is obtained.

A. Bonding Grout :

Get-a-bond	1 LTR.
Water	1 LTR.
Portland Cement	8 KG.

In order to obtain a smooth consistency. The cement should be blended slowly into the liquid. It should be applied with stiff bristle brush.

B. Patching & Repair

Mortar	(6-40m.m Thick)
Cement	50 KG.
Sand	150 KG.
Get-a-bond	10 LTR.
Water	8 LTR.

C. Render Works (6-9m.m per Layer)

Cement	50 KG.
Sand (1.m.m.)	150 KG.
Water	6 LTR.
Get-a-bond	10 LTR.

The render should be semi dry (cohesive consistency).

D. Heavy Duty Floor

Screed	(10-24 m.m Thick)
Cement	50 KG.
3-6 m.m Granite chips	75 KG.
Sand (1.m.m.)	75 KG.
Get-a-bond	10 LTR.
Water	6 LTR.

Screed should be semi dry (cohesive consistency).

E. Bonding Bricks & Tile (6-40 m.m Thick)

Cement	10 KG.
Sand (1.m.m)	25 KG.
Water is adjusted to give a film' mortar	
Get-a-bond	3 LTR.

GTC Paints Company Ltd. W.L.L.

P.O. Box: 24445 Safat - 13105 - Kuwait
Sabhan Tel.: 24710120 - Fax : 24761261
Capital : K.D. 1,000,000 - C.R.: 20117
www.gtcpaints.com



شركة أصباغ جي تي سي المحدودة ذ.م.م

ص.ب: 24445 الصفاة - 13105 - الكويت
صباحان - تلفون : 24710120 - فاكس : 24761261
رأس المال : 1,000,000 د.ك. - س.ت : 20117
E-Mail: sales@gtcpaints.com E-Mail: purchase@gtcpaints.com

CLEANING :

All equipments should be cleaned with water immediately after use.

RECOMMENDATION :

- Any steel trowelling should be very light, with minimum number of passes.
- All applications should be wet, the primer must not be allowed to dry .
- Mixture may need adjustment of water to achieve required consistency.

APPLICATION CONDITIONS :-

At a temperature ranging 5°C (41°F) to 40°C (104 °F) . Relative humidity is below 75%.

STORAGE & HANDLING :-

Product must be stored as per local regulations and should be kept in dry well ventilated location far from heat and direct sunlight. Packing should be tightly closed after use. Mix well before use. Storage temperature range between 5°C (41°F) to 40°C (104 °F).

SAFETY PRECAUTIONS:

The following notes should be considered when using/applying material:-

- (a) Take precautions to prevent material entering the eyes (goggles should be worn, irrigate the eyes with water when become contaminated and obtain medical care at once).
- (b) Take precautions to avoid skin contact (gloves should be worn, barrier cream should be used).
- (c) Ensure that repeated contact of product with skin is avoided.
- (d) Provide adequate ventilation. (Face masks must be worn).
- (e) Keep away from sparks and open flames (for solvent-based materials).

DISCLAIMER:

- ♦ The information given in this data sheet is for guidance only and is done to the best of our knowledge at the date of printing/issuing.
- ♦ GTC reserves the right to change the content of this data without any prior notice.
- ♦ Since we have no control over either the nature or condition of the substrate or different factors which affect the use and application of our products; therefore, no liability can be accepted on basis of this data sheet, unless we specifically agree in writing from us as to the suitability of the recommended product for the intended purpose; and furthermore, application of this product should be carried out under our control and direct supervision.
- ♦ Product data are subject to change without notice and become void five years from the date of issue.
- ♦ If we stop producing above material, the Technical Data Sheet is invalid.

PACKING

- : ♦ 5.5 kg Jerrycan.
- : ♦ 20 kg Jerrycan .

ISSUANCE DATE

: March 2023 .

ORIGIN

: Manufacture in Kuwait By GTC Paints Company Ltd.

ADDRESS

: **GTC PAINTS COMPANY LTD.**

P. O. Box 24445 Safat, 13105 Safat, Kuwait

Tel : 24710120/24710170 - Fax : 24761261 .

Email : sales @ gtcpaints.com